

**TECHNICAL DATA SHEET**
**Product Description:**

F-CHE is a transparent polyester film

It is one side chemically primed other side untreated

**Application:**

Conversion, Metallization

Printing &amp; lamination

FFS machine

**Key Features:**


Very good transparency &amp; clarity

One side chemical coating provide excellent adhesion with various inks &amp; adhesives

Excellent machinability &amp; handling properties

Excellent metal adhesion

Not suitable for hot filling , sterilization and pasteurization

**Film Structure**


PROPERTIES	TEST METHOD (ASTM)	UNIT	TYPICAL VALUE					
			10	12	23	36	50	
THICKNESS	Internal	Micron	10	12	23	36	50	
		(Gauge)	40	48	92	144	200	
FILM DENSITY	D-1505	gm/cc	1.4	1.4	1.4	1.4	1.4	
GRAMMAGE	Internal	gm/m <sup>2</sup>	14.0	16.8	32.2	50.4	70	
YIELD	Internal	m <sup>2</sup> /kg	71.42	59.52	31.05	19.84	14.28	
		in <sup>2</sup> /lb	50318	41934	21876	13978	10060	
TREATMENT LEVEL # (Min) (Chemical coated Side)	D-2578	dyne/cm	60	60	60	60	60	
COEFF OF KINETIC FRICTION (Max) (One side to other side)	D-1894	-	0.50	0.50	0.50	0.45	0.45	
HAZE (Max)	D-1003	%	4.0	4.0	5.0	5.5	6	
TENSILE STRENGTH AT BREAK	MD*	Kg/cm <sup>2</sup>	1900	1900	1900	1750	1750	
	TD*		2000	2000	2000	2000	2000	
TENSILE STRENGTH AT BREAK	MD*	(Psi)	27000	27000	27000	24850	24850	
	TD*		28400	28400	28400	28400	28400	
ELONGATION AT BREAK	MD	%	100	105	115	120	125	
	TD		80	85	90	90	90	
LINEAR SHRINKAGE (Max.) (30 Minute at 150°C)	MD	%	< 3.0					
	TD		< 1.0					
W.V.T.R.(38°C & 90%RH)	(Max.)	F-1249	gm/m <sup>2</sup> /day	40	40	22	15	10
			(gm/100in <sup>2</sup> /day)	2.6	2.6	1.4	0.97	0.6
O.T.R. (23°C & 0%RH)	(Max.)	D-3985	cc/m <sup>2</sup> /day	125	100	70	50	40
			(cc/100in <sup>2</sup> /day)	8.0	6.5	4.5	3.2	2.6

Ref no. QAD UFLI S/10 - F8/1

\*MD = MACHINE DIRECTION \*TD = TRANSVERSE DIRECTION

# The inherent surface tension of the untreated side of any Pet film is minimum 42 dy/cm

**STORAGE & HANDLING:**

FLEXPET™ need to be stocked in a closed warehouse and should not be exposed to direct sunlight or light sources and from humidity. It is recommended to store below 35°C in dry place. FLEXPET™ is suitable for use within 9 month from date of manufacturing, only if material is stored in recommended condition.

**FOOD CONTACT:**

FLEXPET™ complies with EC and FDA regulations on packaging for direct contact with foodstuffs.. Specific document and MSDS are available on request.

**DISCLAIMER:**

It is the responsibility of our customer to determine that their use of our product(s) is safe, lawful, and technically suitable in their intended applications. The Values given in the technical data sheet represent typical values based on the best of our knowledge as on date when the data was compiled. It is offered solely to provide possible suggestions for your own experimentation and not as a guarantee for the material supplied. The user is solely responsible for the end use of the product and needs to perform their own tests to confirm the product suitability / compatibility in all respects. Flex Gives no warranty or accept liability for any loss and fitness of the product for any specific purpose. Flex reserves the right to change the technical data sheet at any time for enhancing the quality of the products without prior information